



## 3.7 Truguard Stabilising Masonry Primer



### DESCRIPTION

Leyland Truguard Stabilising Masonry Primer is a clear solution for binding down powdery residues on exterior masonry surfaces prior to the application of Truguard water-borne masonry coatings.

### Recommended uses

Interior **X** Exterior **✓**

### Type of substrate

Concrete, cement rendering, brick, stone, blockwork and pebbledash.

### Colour range

Clear.

### Finish

N/A

### Volume solid

N/A

### Coverage

1 litre will cover approximately 6 square metres depending on the nature and porosity of the surface.

### Drying time

Touch dry in 1-2 hours. Recoatable after 16-24 hours.

### Transportation and storage

To avoid the risk of spillage, always store and transport in a secure upright position.

**STORE AWAY FROM HEAT AND FLAME.**

### Cleaner

White Spirit.

### VOC content

VERY HIGH VOC CONTENT MORE THAN 50% VOCs (Volatile Organic Compounds) contribute to atmospheric pollution.

EU limit value for this product (Cat A/h): 750 g/l (2007). 750 g/l (2010). This product contains max 750 g/l VOC.

### Film thickness

Wet: N/A

Dry: N/A

*The British Board of Agrément is designated by Government to issue European Technical Approvals based on the assessment of products for construction. Leyland's products carrying this logo have undergone rigorous independent testing and received approval from the BBA.*

**PROFESSIONAL DECORATORS Safety data sheet available on request.**  
Manufactured under a quality system approved by the BSI.

### Preparation

Ensure surface to be painted is sound, clean, dry and free from grease. Treat any mould or lichen with Sterilisation Wash before removing with a scraper or stiff brush, then treat surface again with Sterilisation Wash and allow to dry. Chalky, underbound surfaces, should be thoroughly scraped and dry brushed. Wear a suitable face mask if creating dust.

### Application

Apply by brush one coat of Leyland Stabilising Masonry Primer liberally, brushing the material well into the surface. Allow 16-24 hours to dry, and follow with two coats of the selected Truguard Exterior Masonry Coating. Before applying Truguard Stabilising Masonry Primer to the whole surface, first carry out a test application to a small area. If this dries to a glossy film, thin with one part of White Spirit to two parts of Truguard Stabilising Masonry Primer and then test again in another small area. It is important to ensure that a non-glossy, dried, sealed surface is produced.

### Cleaning

Remove as much product as possible from application equipment before cleaning. Clean equipment immediately after use with white spirit or turpentine substitute. Some local authorities have special facilities for disposal of waste coatings. Do not empty product into drains or watercourses. Replace lid firmly.

### Precautions

PAINT UN.1263

- Contains Solvent naphtha light aromatic.
- Harmful to aquatic organisms.
- May cause long term adverse effects in the aquatic environment.
- Avoid release to the environment.

FLAMMABLE

- Repeated exposure may cause skin dryness or cracking.
- Keep away from sources of ignition – No smoking.
- Ensure maximum ventilation during application and drying.
- Avoid contact with skin and eyes.
- In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- After contact with skin, wash immediately with plenty of soap and water or a recognised skin cleaner – DO NOT USE SOLVENT OR THINNERS.
- If swallowed, seek medical advice immediately and show this container or label.
- Not recommended for interior use on large surface areas – walls, floors or ceilings – or in confined spaces.
- Keep out of the reach of children.