

## Truguard Flexible Exterior Undercoat

Specifically formulated to be used in conjunction with Leyland Truguard Flexible Exterior Gloss to provide an exceptionally flexible, durable and water-resisting gloss system for exterior timber and metal.



The British Board of Agrément is designated by Government to issue European Technical Approvals based on the assessment of products for construction. Leyland's products carrying this logo have undergone rigorous independent testing and received approval from the BBA.

### Recommended uses

Interior  Exterior

### Type of substrate

Softwood, hardwood and plywood panels. Also suitable for use on metal.

### Colour availability

Brilliant White & Dark Grey (2.5ltr & 750ml)

### Finish

N/A

### Volume solid

63%

### Coverage

1 litre will cover approximately 12 square metres depending on the nature and porosity of the surface.

### Drying time

Recoat after 16-24 hours.

### Transportation and storage

To avoid the risk of spillage, always store and transport in a secure upright position. Store away from heat and flame.

### Film thickness

Wet: 85µm

Dry: 53µm

### Preparation

Ensure surface to be painted is sound, clean, dry and free from grease. Avoid the inhalation of dust. Wear a suitable face mask if dry sanding. Special precautions should be taken during surface preparation of pre 1960's paint surfaces over wood and metal as they may contain harmful lead. For further advice contact Technical Advisory on 01924 354354.

**Bare Wood** - Ensure the wood has a moisture content of less than 20%. Treat knots and resinous areas with two thin coats of Knotting Solution. Apply one coat of preservative to all bare timber paying particular attention to end grain and joints. Fill any surface defects, holes or joints using a Two Pack Wood Filler. Apply one coat of Leyland Truguard Flexible Exterior Undercoat followed by two coats of Leyland Truguard Flexible Exterior Gloss.

**Bare Metal** - Remove any rust and corrosion and apply a suitable metal primer. Apply one coat of Leyland Truguard Flexible Exterior Undercoat followed by two coats of Leyland Truguard Flexible Exterior Gloss.

**Previously Painted Surfaces** - for maximum performance, old paint or varnish should be completely removed. **Unsound Condition:** Remove all existing coatings using a hot air stripper or All Purpose Paint & Varnish Remover. Rub down the bare timber using fine waterproof abrasive paper - leaving it in a clean and smooth condition. Then treat timber as per Bare Wood. Wear a suitable face mask when dry sanding. **Sound Condition:** Clean down the surface with Sugar Soap and abrade - to ensure maximum protection apply one coat of Truguard Flexible Exterior Undercoat followed by two coats of Truguard Flexible Exterior Gloss, allowing 16-24 hours between coats.

### Application

Stir well before use. Do not thin. Suitable for application by brush or roller.

### Cleaning

Remove as much product as possible from application equipment before cleaning. Clean equipment immediately after use with white spirit or turpentine substitute. Some local authorities have special facilities for disposal of waste coatings. Do not empty product into drains or watercourses. Replace lid firmly.

### Warning

- Keep out of reach of children.
- Avoid contact with skin and eyes.
- Do not ingest.
- If medical advice is needed have container or label to hand.
- Please refer to Product Label & Safety Data Sheet (SDS) for hazard warnings and information on safe handling/use/transport/storage/disposal/emergency.
- SDS available: [www.leylandtrade.com](http://www.leylandtrade.com) or call 01924 354354