



3.6 Truguard Flexible Exterior Undercoat



DESCRIPTION

Specifically formulated to be used in conjunction with Leyland Truguard Flexible Exterior Gloss to provide an exceptionally flexible, durable and water-resisting gloss system for exterior timber and metal.

Recommended uses

Interior Exterior

Type of substrate

Softwood, hardwood and plywood panels.
Also suitable for use on metal.

Colour range

White and a selection of ready mixed colours.

Finish

N/A

Volume solid

69%

Coverage

1 litre will cover approximately 12 square metres depending on the nature and porosity of the surface.

Drying time

Touch dry in 4-6 hours. Recoatable after 16-24 hours.

Transportation and storage

To avoid the risk of spillage, always store and transport in a secure upright position.
STORE AWAY FROM HEAT AND FLAME.

Cleaner

White Spirit.

VOC content

HIGH VOC CONTENT 25-50%

VOCs (Volatile Organic Compounds) contribute to atmospheric pollution.

EU limit value for this product (Cat A/d): 400 g/l (2007).
This product contains max 400 g/l VOC.

Film thickness

Wet: 83µm

Dry: 58µm

The British Board of Agrément is designated by Government to issue European Technical Approvals based on the assessment of products for construction. Leyland's products carrying this logo have undergone rigorous independent testing and received approval from the BBA.

PROFESSIONAL DECORATORS Safety data sheet available on request.
Manufactured under a quality system approved by the BSI.

Preparation

Ensure surface to be painted is sound, clean, dry and free from grease. Remove all loose and defective paint. Rub down sound glossy surfaces with fine waterproof abrasive paper to provide a key. Avoid the inhalation of dust. Wear a suitable face mask if dry sanding. Treat any mould or lichen with sterilisation wash as directed. For maximum performance, old paint or varnish should be completely removed. Treat new or bare timber surfaces with clear preservative, prime metal surfaces with an appropriate primer. Follow with a coat of Leyland Truguard Flexible Exterior Undercoat then two coats of Leyland Truguard Flexible Exterior Gloss. Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead. For further advice contact Technical Advisory.

Application

Stir well before use. Do not thin. Suitable for application by brush or roller.

Cleaning

Remove as much product as possible from application equipment before cleaning. Clean equipment immediately after use with white spirit or turpentine substitute. Some local authorities have special facilities for disposal of waste coatings. Do not empty product into drains or watercourses. Replace lid firmly.

Precautions

PAINT PRODUCT
FLAMMABLE

- Contains Ethyl Methyl Ketoxime. May produce an allergic reaction.
- Repeated exposure may cause skin dryness or cracking.
- Keep away from sources of ignition – No smoking.
- Ensure maximum ventilation during application and drying.
- Avoid contact with skin and eyes.
- In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- After contact with skin, wash immediately with plenty of soap and water or a recognised skin cleaner – DO NOT USE SOLVENT OR THINNERS.
- If swallowed, seek medical advice immediately and show this container or label.
- Keep out of the reach of children.